



Gesong Enterprises Co., Ltd.

Bond Virtually any substrate faster, safer and more effectively.

Cost down and eco-friendly

GESONG HEAT SEAL ADHESIVE is a high-performance bonding agent designed to bond virtually any substrate faster, safer, and more effectively than traditional adhesive systems. Because GESONG heat-activated film adhesives are so easy to use, they reduce manufacturing costs and increase productivity dramatically in a variety of manufacturing applications.

Gesong Heat adhesive films are applied to most fabrics, building materials, industry & electronic groups. We have 3 different types of heat seal adhesive film.

Textiles: Embroidery, Label, Zipper, Viscosity Buckle, most fabrics ... etc

Building Materials: Aluminum, Iron, Plastic, PVC and Wood ... etc Industry & Electronics: Lead frame, Memory Card, Heat Sink ... etc

Nowadays, we can use UV ink for printing pictures on our heat adhesive films. Any pictures you like can be printed on clothes, plastics(e.g. PU, PVC), and metals(e.g. steel, iron, aluminum). This new technology can reduce production costs and keep the process simple. It's a new idea to make your own style.

GESONG ENTERPRISES CO., LTD.

ADD: 5F,No.57, Min-Sheng E. Rd., Sec.3, Taipei 104, Taiwan

TEL: 886-2-2505-5101/2 FAX: 886-2-2505-6858

E-MAIL: Hot-melted Films, Machine: ted@gesong.tw

巨松熱壓黏膠膜 GESONG HEAT SEAL ADHESIVE FILM

巨松企業始終在追求進步,追求卓越,我們的產品使用 生產迅速,不但能減少成本,產品也符合環保規定,品質穩定 以熱熔貼合的方式,替代傳統複雜的縫合,大幅增加了衣物的 舒適度與伸展性。 GESONG HEAT SEAL ADHESIVE are high performance bonding agents designed to bond virtually any substrate faster, rafer and more effectively than tranditional adhesive systems. Because GESONG hear application adhesive are so easy to use, they reduce manufacturing systems increase productivity dramatically in a variety of manufacturing applications.



我們現已研發將UV噴墨直接噴塗在熱熔膠上,可以將任何您喜歡的圖案印上去,直接貼在紡織布類、塑膠類(PU、PVC等),更可以直接貼合於金屬(銅、鋁、鐵等)產品,這個新科技可以降低生產成本,而且讓製程變得更簡單,給你一個全新的想法讓你打造自己的風格。

Nowdays, we can use UV ink for printing pictures on our heat adhesive films. Any pictures you like can be printed on clothes, plastics (e.g. PU, PVC) and metals (e.g. steal, iron, aluminum). This is a new technology can reduce the production costs and keep the process simple. It's a new idea to make your own style.



GESONG ENTERPRISES CO., LTD.

(104) 5F, No. 57, Sec. 3, Min Sheng E. Rd., Taipei, Taiwan. TEL: +886-2-25055101~2 or 25025268 FAX: +886-2-25056858

E-mail: jason@gesong.tw WEB: www.gesong.tw



布與鋁片 PVC與木材貼合 工業及電子類: PCMCIA CARD SMART CARD MEMORY CARD HEAT SINK 導線架 麥拉鋁片

2 Building materials

尚有其它特殊用途 歡迎洽詢 本公司特設計佈部門 為您解決專業問題 如需黏著試驗 請提供樣品物件以代測試



ADD: (104)5F, No.57, Sec.3 Min Sheng E. Rd., Taipei, Taiwan E-MAIL: gesong@seed.net.tw

TEL: 886-2-25055101~5 or 25025268~9

FAX: 886-2-25056858 or 25025864

巨松企業GESONG - "熱融膠膜"產品說明書

型號	材質	用途	厚度	長度	第幅	軟化溫度	貼今溫度
G306	聚酰胺	刺繡臂章、繡花產品、	0.06mm (0.002")	200M			\
G308	POLYAMIDE	布料、鐵標等	0.08mm (0.003")	200M	92CM		
G310	尼蔻(NYLON)	纺織品貼合	0.10mm (0.004")	100M	(36")	94°C~99°C	170°C~200°C
G312	(Film + Paper)	同材質NYLON貼合用	0.12mm (0.005")	100M			
G318			0.18mm (0.007")	100M			
GN506	聚酯	拉鍊、滴塑標、	0.06mm (0.002")	100M			
GN508	POLYESTER	PVC & TPU微量射出商標、	0.08mm (0.003")	100M	92CM	110°C~120°C	160°C~180°C
GN510	(Film + Paper)	布料紡織品…等	0.10mm (0.004")	100M	(36")		
GN512		同材質POLYESTER貼合用	0.12mm (0.005")	100M			
G606	聚氯乙烯	彈性布料產品、	0.06mm (0.002")	100M			
G608	POLYURETHANE	内衣褲、部分潑水布料、	0.08mm (0.003")	100M	92CM	115°C~120°C	115°C~120°C 170°C~180°C
G610	(PU)	纺織品貼合…等	0.10mm (0.004")	100M	(36")		
G612	(Film + Paper)	同材質PU貼合用	0.12mm (0.005")	100M			
G1606	聚氯乙烯	PVC & TPU微量射出商標、	0.06mm (0.002")	100M			
G1608	POLYURETHANE	黏扫帶、泡棉、	0.08mm (0.003")	100M	92CM	77°C~80°C	130°C~160°C
G1610	(PU)	部分潑水布料…等	0.10mm (0.004")	100M	(36")		
G1612	(Film + Paper)	同材質PU貼合用	0.12mm (0.005")	100M			
	聚酰胺	汽車内裝座椅、皮製品、	18g/m²	100Y			
PA8001	POLYAMIDE	内衣褲產品、泡棉、	23g/m²	100Y	44" & 60"	2,06~ 2,08	100°C~140°C
(NATON)	(Film + Paper &	玻璃纖維、多數紡織品	30g/m²	100Y			
尼離	without paper)	窗簾布料…等	35g/m²	100Y			

如需貼合測試,請提供樣品物件代為測試。 本公司備有詳細資料歡迎來電洽詢。

巨松企業股份有限公司

台北市中山區民生東路3段57號5樓 FAX: 886-2-2505-6858

TEL: 886-2-2505-5101/2 FAX E-MAIL: ted@gesong.tw WEB SI

WEB SITE: www.gesong.tw

巨松熱融膠膜的使用説明

Instruction of Using GESONG Heat Seal Adhesive Film (for industry)

所需材料與器材:

- 1. 巨松熱融膠膜
- 2.無經過離型、波水或特殊處理的刺繡品
- 3. 適用於此種貼合的熱壓機
- 4.電熱刀或裁刀

Materials and Equipments:

- 1. GESONG Heat Seal Adhesive Film
- Embroidery without releasing agent, waterproof, or other chemical treatment.
- 3. Hot Press Machine for this special purpose.
- 4. Hot Cutter or Normal Cutter to melting or separate the edge.

A.與刺繡徽章的貼合流程 Procedures for Adhering our Film on Embroidery



1. 準備欲背膠的刺繡徽章(無經過離型、波水或特殊處理)。

Prepare the embroidery (badge) without releasing agent, waterproof, or other chemical treatment.



2. 將徽章的正面朝下置於機器平台上。取一段適當大小的巨松熱融膠膜。

Place the embroidery on platform of the machine with the reverse side up. Cut a proper size from GESONG HSA Film.




3. 將巨松熱融膠膜完全覆蓋於徽章的背面。 (膠膜的離型紙面需朝上、膠膜面朝下) Fully cover GESONG HSA Film (with the film side down and the releasing paper side up) on the reverse side of the embroidery.



4. 將徽章與膠膜置於機器平台上。設定溫度為100°C。啟動機器,降下熱壓板面。 Leave them on the platform at proper position. Set the temperature at 100°C (about 212°F) Start the machine.



5. 加熱時間為5秒到8秒之間。 Wait for 5 to 8 seconds.




6. 加熱完成,升起熱壓板面。 Heating finished. Stop the machine.



7. 徽章完成背膠。 Adhered.



8. 使用電熱刀將徽章與多餘的膠膜分離。 Separate the extra film by a hot cutter.



9. 背過膠的徽章已完成。 The embroidery adhered with GESONG HSA Film has finished.

B.上過膠的徽章與布料的貼合流程 Procedures for Adhering Filmed Embroidery on Fabrics



1. 撕下徽章背面的離型紙。 Tear of the releasing paper of the filmed embroidery.



2. 準備欲背章的衣服或布料。 Prepare the clothes or fabrics for adhesion.



3. 將衣服放置於熱壓機的平台上,衣服需背 章的面朝上,對準加熱的部位。 Place the clothes (with the side for adhesion up) at the proper position of the platform of the hot pressing machine.




4. 將已撕下離型紙的徽章放置在欲貼合於 衣服上的位置。 Place the embroidery (without the releasing paper) at the wanted position of the clothes.




降下熱壓板面。 Set that temperature between 170°C to 204°C (about 338°F to 399°F). Start the hot pressing.



6. 加熱時間為10秒到20秒之間。 Wait for 10 to 20 seconds.



7. 加熱完成,升起熱壓板面。 Heating finished. Stop the machine.



8. 徽章與衣服的貼合完成。 Adhesion finished.





GESONG ENTERPRISES CO., LTD. www.gesong.com 巨松企業股份有限公司 www.gesong.com.tw 總公司: (104)台灣台北市民生東路3段57號5樓 電子信箱: gesong@seed.net.tw

ADD: (104)5F, No.57, Sec.3 Min Sheng E. Rd., Taipei, Taiwan E-MAIL: gesong@seed.net.tw

GESUNG TEL: 886-2-25055101~5 or 25025268~9 FAX: 886-2-25056858 or 25025864